

Sikafloor® 105

Epoxy Epo-Rok Mortar Primer

Description	A two-component, penetrating high solids, light amber, epoxy-based primer/bond coat.
Where to Use	Designed for use as a primer/bond coat specifically in conjunction with Sikafloor Epo-Rok® epoxy mortar system. Formulated to penetrate and reinforce the concrete substrate in addition to ensuring a tenacious bond between the Sikafloor Epo-Rok epoxy mortar and the concrete floor.
Advantages	<ul style="list-style-type: none"> ■ Excellent wetting properties. ■ Ensures good bond between substrate and Sikafloor Epo-Rok Mortar. ■ Improves trowelability of epoxy mortar. ■ Seals substrate, reducing the risk of pinholes.

How to Use

Surface Preparation	<p>Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be dressed off to achieve a level surface prior to the application. Concrete should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by shot blasting or equivalent mechanical means. (CSP-3 as per ICRI guidelines). Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate. Whenever "shot-blasting" is utilized, be careful to leave concrete with a uniform texture. Over "blasting" will result in reduced coverage rates of the primer and/or subsequent topcoats.</p> <p>The compressive strength of the concrete substrate should be at least 3500 psi (24 MPa) at 28 days and at least 250 psi (1.7 MPa) in tension at the time of application of Sikafloor 105.</p>
----------------------------	--

Mixing	<p>For bulk packaging when not mixing full units each component must be pre-mixed separately to ensure product uniformity.</p> <ol style="list-style-type: none"> 1. Carefully empty the contents of the Part "H" Hardener entirely into the can of Part "R" Resin. 2. Product should be mixed using a "Jiffy Mixer" and a slow speed drill (300-450 rpm) to minimize entrapping air. Mix until completely blended. This will take about 1-1/2 to 2 minutes be careful to mix the contents completely to avoid weak spots in the primer. During the mixing operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing. Mix only that quantity that can be used within its pot life.
---------------	--

Application	<p>Using a flat squeegee and high quality 3/8" nap roller, apply Sikafloor 105 evenly at the rate of 800-1,200 sq. ft. (74.3 - 111.5 m²) per 4.8 gallon kit. Avoid leaving puddles in rougher areas. The application of the Epo-Rok Mortar should begin soon after the Sikafloor 105 mortar primer is applied. If Sikafloor 105 is allowed to become tack free, the surface must be reprimed before application.</p>
--------------------	---

Typical Data

Coverage	Approximately 800-1,200 sq. ft. (74.3 - 111.5 m ²) per 4.8 gallon kit over properly prepared concrete floor.
Pot life	Approximately 30 minutes if applied as indicated above at 75°F (24°C). There is approximately 2 hours open time after the primer is applied before it will become too firm to adhere to.
Shelf Life	2 years in original unopened container under proper storage conditions. Store dry between 40° - 90°F (5° - 32°C).
VOC (g/l)	ASTM D2369-07 12.0 g/l
Packaging	Sikafloor 105 is packaged in kits as pre-proportioned batches for easy jobsite mixing and application. Each two batch unit consists of 2 loose 5 gallon pails of Part "R" Resin and 2 one gallon cans of Part "H" Hardener which are packed together in a corrugated box. The contents of one can of Part "H" are completely added to the contents of one pail of Part "R". The pail is oversized for mixing. Each mixed batch contains 2.4 gallons, 4.8 gallons per two-batch kit.

Limitations	<ul style="list-style-type: none"> ■ Minimum/Maximum substrate temperature: 60°F/85°F (15.5°C/30°C). ■ Maximum relative humidity: 85%. ■ Substrate temperature must be at least 5°F (3°C) above measured dew point. ■ Conduct quantitative anhydrous calcium chloride testing in accordance with ASTM-F1869. Maximum acceptable test result is 3 pounds per 1,000 ft² per 24 hours. Determine the surface moisture content by using an impedance moisture meter designed for use on concrete as detailed in ASTM E-1907. Acceptable test results shall be 4% by mass or less. If over, use Sikafloor EpoCem 81/82 or Sikafloor Vapor Block. ■ Do not use on exterior, on-grade substrates. ■ Terminate at shoulders cut into substrate, avoid feather-edging. ■ Freshly applied Sikafloor 105 should be protected from dampness, condensation and water for at least 24 hrs. ■ Do not thin this product. Addition of thinners will slow the cure and reduce the ultimate properties of this product. Critical recoat times will also be affected. ■ This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the resurfacer. ■ Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. UV resistant, light stable topcoats are available where ultimate color/clarity retention is required.
Caution	<p>COMPONENT R: WARNING - IRRITANT, SENSITIZER: Contains epoxy resins, Furfuryl Alcohol (CAS 98-00-0). Eye irritant. May cause skin/respiratory irritation. Prolonged and/or repeated contact with skin may cause allergic reaction/sensitization. Deliberate concentration of vapors for purposes of inhalation is harmful and can be fatal. Harmful if swallowed. Strictly follow all use, handling and storage instructions.</p> <p>COMPONENT H: WARNING: CORROSIVE, SENSITIZER, IRRITANT. Contains amines (mixture), bisphenol A (CAS 80-05-7). Contact with skin and eyes causes severe burns. Respiratory irritant. May cause eye/skin irritation. Possible skin sensitization/allergic reaction with prolonged or repeated exposure. Harmful if swallowed. Deliberate concentration of vapors for purposes of inhalation is harmful and can be fatal. Strictly follow all handling, use and storage instructions.</p>
First Aid	<p>Eyes – Hold eyelids apart and flush thoroughly with water for 15 minutes. Skin – Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. Inhalation – Remove to fresh air. Ingestion – Do not induce vomiting. Dilute with water. Contact physician. In all cases contact a physician immediately if symptoms persist.</p>
Handling and Storage	<p>Wear protective equipment (gloves/safety glasses/clothing) to prevent contact with skin and eyes. Keep container closed in a cool dry place. Wash skin thoroughly with soap and water after use. Use with adequate, general and local, exhaust ventilation. In absence of adequate ventilation, use a properly fitted NIOSH respirator. Remove contaminated clothing. Launder before reuse. Store in cool dry well ventilated area with container closed.</p>
Clean Up	<p>Avoid direct contact with eyes and skin. Wearing chemical resistant goggles/gloves/clothing, collect spill. Ventilate area. In absence of adequate ventilation, use properly fitted NIOSH respirator. Sweep up spill and place in closed container. Dispose of in accordance with applicable local, state and federal environmental regulations.</p>
Additional Info	<p>Technical Data Sheets are updated periodically. To ensure the most current version is being used, visit Technical Resources on www.sikafloorusa.com. Proper material application is the responsibility of the user. Site visits made by Sika personnel are for making technical recommendations only and not for supervising or providing quality control. Before applying for protection against specific chemical environments, consult Chemical Resistance Guide or Sika Technical Service.</p>

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikacorp.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikaconstruction.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikaconstruction.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

