

Sikafloor® Merflex 90

Description	Sikafloor Merflex 90 is a monolithic, flexible, and abrasion resistant flooring system that is designed for areas requiring a combined water protection membrane and wearing surface. It consists of a prime coat of Sikafloor 265, a two component, high solids and flexible epoxy for use as a flexible membrane, a base coat of Sikafloor 265 broadcasted with quartz aggregate, and sealed with Sikafloor 215, a two component high solids, low viscosity, clear epoxy topcoat. Sikafloor 265 is a true elastomer for use as a seamless, waterproofing membrane. This unique, flexible polymer system maximizes flexibility and elongation to provide excellent crack bridging capabilities. Can be used alone as a Clear or with Sikafloor Epoxy Color Additive.
Where to Use	<ul style="list-style-type: none"> ■ Mechanical equipment rooms ■ Interior floor spaces where humidity & temperature are micro-controlled ■ Access floor systems for computer rooms and offices where liquid lines prevail ■ Areas requiring an elastomeric water protection surface that can accept heavier traffic
Advantages	<ul style="list-style-type: none"> ■ Lower maintenance and life cycle cost vs. tile, sheet goods, and carpet ■ Tough, durable and seamless floor ■ Performance benefits of both an elastomeric membrane & a wearing surface combined in one system ■ Excellent crack bridging capabilities.
Chemical Resistance	Before applying for protection against specific chemical environments, consult Sikafloor 215 Chemical Resistance Guide or refer to the Chemical Resistance Guide of the top coat applied or contact Sika Technical Services at 800-933-SIKA (7452).
How to Use	
Surface Preparation	Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be dressed off to achieve a level surface prior to the application. Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by shot blasting or equivalent mechanical means. (CSP-3 as per ICRI guidelines). Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate. Whenever "shot-blasting" is utilized, be careful to leave concrete with a uniform texture. Over "blasting" will result in reduced coverage rates of the primer and/or subsequent topcoats. It is also possible that the texture of the "shot-blast pattern" may show through the last coat. This is known as "tracking". The compressive strength of the concrete substrate should be at least 3500 psi (24 MPa) at 28 days and at least 250 psi (1.7 MPa) in tension at the time of application of Sikafloor 265.
System Coverage	<p>Primer: Sikafloor 265: Sikafloor 265 pigmented applied at 20 mils (80 sq.ft. per gallon).</p> <p>Broadcast Coat: Sikafloor 265: Sikafloor 265 pigmented applied at 20 mils (80 sq.ft. per gallon) and broadcasted to refusal with 35 mesh sand or colored quartz aggregate.</p> <p>Top Coat: Sikafloor 215: Sikafloor 215 pigmented at 15 mils (105 sq.ft. per gallon).</p>
Cure Mechanism	<p>Primer Coat & Broadcast Coat: Sikafloor 265 Pigmented: At 75°F (24°C), the primer coat and broadcast coat should be ready for foot traffic within 12 hours.</p> <p>Groutcoat: Sikafloor 215; At 75°F (24°C), the body coat should be ready for foot traffic within 12 hours.</p>

Typical Data (Sikafloor 265)

Hardness (Shore D)	ASTM D-2240	40
Adhesion, Bond Strength	ASTM D-4541	520 lbs/in ² -Concrete Failure
Impact Resistance: (Gardener Impact Tester)	ASTM D-2794	>160 in – lb (18.1 N-m)
Flammability	ASTM D-635	Self Extinguishing
Tensile Strength	ASTM D-638	1050 psi (7.2 MPa)
Tensile Elongation	ASTM D-638	125%
Modulus of Elasticity	ASTM D-638	246,000 psi (1697 MPa)
Tear Strength	ASTM D-1938	90 lbs (0.4003399)
Thermal Cycling: 24 hrs.	ASTM C-884	No Cracking
-5.8°F-77°F; -21°C to 25°C		
Above typical values based on 7 days cure @ 75° F (24° C)		



<p>Mixing</p>	<p>Primer Coat and Broadcast Coat: Sikafloor 265 Pigmented: For bulk packaging when not mixing full units each component must be pre-mixed separately to ensure product uniformity. It is important to remember that the Sikafloor 265 has a limited pot life. Review that all surface preparation is complete and application equipment is in good working order, before starting the mixing sequence.</p> <p>Color Additives: If color is desired, the appropriate Sikafloor Epoxy Color Additive is added to the “Clear” Part R resin 1 pint of Epoxy Color Additive to 1 mixed gallon of Sikafloor 265. Mix at low speed for a minimum of two minutes.</p> <ol style="list-style-type: none"> 1. The Part R Resin must be thoroughly mixed prior to the addition of Part H Hardener. 2. Mix ratio is 1 Part Resin to 1 Part Hardener by volume. Pour into an empty clean pail correct amount of Resin and Hardener, 1 R:1 H. 3. Mix with a very low speed jiffy mixer, until completely blended. This will take about 2 to 3 minutes. Be careful not to introduce any air bubbles while mixing. 4. Due to the difference in viscosity between the Part “R” Resin and Part “H” Hardener, care must be taken to ensure that both components are thoroughly mixed in order to avoid weak or partially cured spots in the coating. 5. Since this product does not need any induction time, it should be used immediately after mixing. <p>Top Coat: Sikafloor 215 Pigmented: For bulk packaging when not mixing full units each component must be pre-mixed separately to ensure product uniformity. It is important to remember that this coating has a limited pot life. Therefore it is recommended to check and make sure everything is in order before starting the mixing sequence. For 15 and 165 gallon kits, add two parts Resin (Part R) and one part Hardener (Part H) by volume to a clean mixing container. Do not count Epoxy Color Additive in the volume ratio. Color Additives: If color is desired, the appropriate Sikafloor Epoxy Color Additive is added to the “Clear” Part “R” Resin at one quart per three mixed gallons. Refer to the Epoxy Color Add Data Sheet for specific ratios. Mix at low speed for a minimum of two minutes.</p> <ol style="list-style-type: none"> 1. Carefully empty the contents of the Part “H” Hardener entirely into the can of Part “R” Resin. The Part “R” container is oversized to allow for easy mixing (3 gallon kit only). 2. Mix with a very low speed jiffy mixer, until completely blended. This will take about 2 to 3 minutes. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in coating. During the mixing operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing. Mix only that quantity that can be used within its pot life.
<p>Application</p>	<p>Primer Coat and Broadcast Coat: Sikafloor 265: Apply by first pouring a bead of material in the form of a ribbon on the surface to be coated. The material should not be left in the container too long because it will set faster thus reducing the pot life. Using a notched squeegee, spread the bead of material at a rate of approximately 80 square feet per gallon. Apply as evenly as possible, working from left to right, and then back. Back roll using a high quality 18”, 3/8” nap roller and/or looped roller depending on thickness and desired finish. Broadcast the second coat with neutral 35 mesh sand OR decorative quartz aggregate depending on the desired finished look.</p> <p>Top Coat: Sikafloor 215: This product should be applied by first pouring a bead of material in the form of a ribbon on the surface to be coated. The material should not be left in the container too long because it will set faster thus reducing the pot life.</p> <ol style="list-style-type: none"> 2. Using a flat or notched squeegee, spread the bead of material at a rate of approximately 105 sq. ft. per gallon. Apply as evenly as possible, working from left to right, and then back. 3. Back roll using a high quality 18”, 3/8” nap roller. 4. Roll with a plastic loop roller after 10 minutes to remove excess bubbles.
<p>Limitations</p>	<ul style="list-style-type: none"> ■ Minimum/Maximum substrate temperature: 60°F/85°F (15.5°C/30°C). ■ Maximum relative humidity: 85%. ■ Substrate temperature must be 5°F (3°C) above measured dew point. ■ Conduct quantitative anhydrous calcium chloride testing in accordance with ASTM-F1869. Maximum acceptable test result is 3 pounds per 1,000 ft² per 24 hours. Determine the surface moisture content by using an impedance moisture meter designed for use on concrete as detailed in ASTM E-1907. Acceptable test results shall be 4% by mass or less. If over, use Sikafloor EpoCem 81/82. ■ Freshly applied Sikafloor 265 and 215 should be protected from dampness, condensation and water for at least 24 hours. ■ This product is not designed for exterior use, immersion, or any use where moisture can reach the underside of the coating. ■ Do not thin this product. Addition of thinners will slow down the cure and reduce the ultimate properties of this product. ■ Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. UV resistant, light stable topcoats are available where ultimate color/clarity retention is required.

Industrial Flooring

Additional Info

Sikafloor System Sheets describe a series of Sikafloor products installed in progression. For specific information on the individual products mentioned, including, Mixing, Application, Chemical Warnings, First Aid, Handling & Storage, and Clean Up, PLEASE REFER TO THE INDIVIDUAL PRODUCT'S TECHNICAL DATA SHEET, available at www.sikafloorusa.com. System sheets are updated periodically. To ensure the most current version is being used, visit Technical Resources on www.sikafloorusa.com. Proper material application is the responsibility of the user. Site visits made by Sika personnel are for making technical recommendations only and not for supervising or providing quality control. Before applying for protection against specific chemical environments, consult Chemical Resistance Guide or Sika Technical Service.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikacorp.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at www.sikafloorusa.com or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BELIEABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at www.sikafloorusa.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

The Sika logo consists of the word "Sika" in a bold, italicized, sans-serif font, with a registered trademark symbol (®) to its right. The text is white and is set against a red triangular background that points downwards.